

Natalia S. Hrudkina

Associate Professor
Department of Mathematics and Modeling
Donbass State Engineering Academy
Ukraine

Oleg E. Markov

Professor
Department of Computerized Design and
Modeling of Processes and Machines
Donbass State Engineering Academy
Ukraine

Alexander A. Shapoval

Associate Professor
Department of Manufacturing Engineering
Kremenchuk Mykhailo Ostohradskiy
National University
Ukraine

Viacheslav A. Titov

Professor
Department of Aircraft Manufacturing
Technology
National Technical University of Ukraine
"Igor Sikorsky Kyiv Polytechnic Institute"
Ukraine

Igramotdin S. Aliiev

Professor
Department of Metal Forming
Donbass State Engineering Academy
Ukraine

Payman Abhari

Professor
Department of Metal Forming
Donbass State Engineering Academy
Ukraine

Khrystyna V. Malii

Assistant Professor
Department of Metal Forming
Donbass State Engineering Academy
Ukraine

Mathematical and Computer Simulation for the Appearance of Dimple Defect by Cold Combined Extrusion

The article is considered a comparative analysis for predicting defect such as dimple by energy method of power balance, upper bound method and finite element method. The upper bound method takes into account the geometrical position and dimension of the dimple, the criterion for the formation in dimple by energy method of power balance is the presence of a minimum point in the function of relative pressure on the relative velocity of metal outflow in the vertical direction. New engineering calculations for the relative pressure are developed in combined radial-backward extrusion process by using a kinematic module with fillet. A comparative analysis of the obtained data has been carried out by energy method of power balance, upper bound method, computer simulation by Qform 2/3D program and experimental data. Rationality of using the energy method of power balance in view of its efficiency and the possibility of taking into account various friction conditions and the presence of fillet on the matrix, as well as smaller deviations from the results of finite element simulation and experimental data have been defined. Providing more conditions that are favorable for friction in the bottom of the billet and in the flange area in comparison with the friction conditions on the glass wall contribute to delay in the dimple appearance. It was found that the radius of fillet makes it possible to delay the dimple appearance by the approximately $(0,4 \div 0,5R)$ mm for the entered radius of fillet R . This allows us to expand the possibilities of obtaining parts with a flange by combined radial-backward extrusion without the formation of a defect such as dimple.

Keywords: energy method of power balance; upper bound method; Finite element method; kinematic module; combined extrusion; dimple.

1. INTRODUCTION

In modern conditions, mechanical engineering has one of the key roles in ensuring the development of the economic. In this context, the priorities are determined by the development of over-modern science-intensive technologies as opposed to the classical methods of forming parts by removing shavings [1, 2]. The availability of different methods by metal forming, it is possible to solve the actual problem based on economic rationality [1, 3-6]. In recent years, investigation has been carried out in the direction of solving specific practical problems [3, 5-9] and the development of theoretical foundations by different methods such as energy method of power balance and upper bound method based on modeling of plastic deformation processes, finite element methods and statistical data analysis [10-13]. Areas of theoretical investigations

including such as methods for describing the shape of bodies, components of design schemes, effective techniques for simplifying the assessments of power modes, predicting the phased shaping of a semi-finished product, determination of the optimal shape of the tool and techniques to avoid defect formation [11, 12, 14-17]. Cold forging extrusion process is considered such as perspective process of metal forming that allows us to use different billets and to make parts with different dimensions and qualities [1, 2, 18-21]. However, the limiting factors of more active implementation for cold forging extrusion processes in production are the failure of recommendations for predicting power and deformation mode. On the other hand, for cold extrusion forging processes according to basic schemes such as combined extrusion processes with several metal flow freedom degrees, additionally need to solve the problems of predicting the step by step and limiting shaping of the semi-finished product and also under certain conditions to appear and avoid defect formation processes [12, 13, 22-27]. The main ones are the non-fulfillment of the shape and size in the finished product, ruptures (separation) of the flange, the formation of cracks and various types of defects such as walls

Received: August 2021, Accepted: October 2021

Correspondence to: Dr Natalia S. Hrudkina
Donbass State Engineering Academy, Akademichna
(Shkadinova) Str. 72, 84313 Kramatorsk, Ukraine
E-mail: vm.grudkina@gmail.com

doi: 10.5937/fme2201090H

© Faculty of Mechanical Engineering, Belgrade. All rights reserved

FME Transactions (2021) 50, 90-98 90

curvature, squeeze, flange and dimple [28-31]. Therefore, the actual problems are determination of ratios that are critical from the viewpoint of possible defect formation and technological factors that allows us to avoid the appearance of a defect. This will significantly expand the scope of application in cold forging extrusion technologies, including for combined extrusion with several metal flow freedom degrees.

At the present time investigation of cold forging extrusion processes based on schemes and with several metal flow freedom degrees are devoted to investigation [11, 12, 15, 17-31]. Most of the investigation in modeling combined extrusion processes including the determination of the force regime, estimates in increments of semi-finished product and carried out based on finite element modeling and experimental investigations [18, 19, 23, 25]. The authors [12, 13, 23-26, 28] has determined the influence of the tool design features, geometric relationships for shaping and energy power parameters in combined radial-longitudinal extrusion processes, however, the question of the possible appearance of defect formation has not been put. Investigation can be considered a separate area by deformability of billets, calculations of the plasticity resource for the processes of combined radial-longitudinal extrusion [14, 16]. This makes it possible to assess the expansion of the technological capabilities in the investigated plastic deformation processes. On the other hand, the promising application of various modifications in the energy method of power balance and upper bound method such as for determining energy-power parameters, and for predicting the formation of a semi-finished product and defect formation are considered [27, 30, 31].

Major defects in the processes of cold forging extrusion can be attributed such as walls curvature (Fig. 1, a), squeeze and dimple (Fig. 1, b, c, d), non-adherence and rupture of the flange (Fig. 1, e) [16, 27, 29, 30]. Defects in the form of the end lateral curvature occur due to insufficient fixation of the punch in the deformation process, which also causes a difference in the thickness of the glass wall (Fig. 1, a). Defect formation such as flange rupture is typical, usually for low plastic materials or with a small flange thickness for more plastic materials (Fig. 1, e). This type of defect formation is facilitated by a rather complex stress-strain state diagram, since in the flange formation zone circumferential tensile stresses prevail on the peripheral part and so the stress state is close to linear tension. Shape deviation in the form of dimple defect, depending on the extrusion schemes, can occur at different stages of the process and in different zones of the semi-finished product. For combined radial-backward extrusion in hollow parts with flange in the final stage of the process, with the overwhelming flow of metal in the opposite direction, dimple defect is formed in the bottom section (Fig. 1, c). For the same process, under the condition of the overwhelming metal flow in the radial direction (glass wall does not change) dimple defect is formed on the inner wall of the glass. (Fig. 1, d). The works [27, 29, 30] have been demonstrated the possibilities of using the energy method of power balance, upper bound method and finite element method for predicting defect formation in the processes of

combined radial-longitudinal extrusion. Previously reported investigations [27, 30] have been demonstrated the capabilities of the upper bound method for predicting dimple defect by comparative analysis with experimentally obtained data. However, the upper bound method has been given overestimated data in the moment of dimple formation and has been used for a simple case without taking into account the influence of friction conditions and the presence of chamfers or fillets on the matrix. In investigation [29], an analysis of experimental data in the deformation force for a process without and with dimple formation has been presented. However, the die design features with the form of a chamfer or fillet on the die tools and the right choice with friction conditions are very important in the extrusion processes to delay in the defect appearance. The energy method of power balance, which has been developed in recent years, is aimed at solving axisymmetric processes and is more flexible to quickly change the configuration of the tool and take into account the friction conditions. The development of the energy method will expand the understanding of the conditions for the appearance of a defect and determining the factors of effective control in the shaping of a semi-finished product for a more complex configuration.




Figure 1. Flange defects with the form of walls curvature(a), squeeze (b) dimple (c), (d) and rupture (e) [27, 29]

2. PRESENTATION OF THE MAIN MATERIAL

2.1 Mathematical modelling of the defect formation process by the energy method of power balance and upper bound method

The energy method of power balance and upper bound method are currently presented in two of the most common forms: upper bound method (plane strain problem) and energy method of power balance (axisymmetric problem) [32-40]. Approaches to solve problems for determining conditions, position and main factors in extrusion processes with the presence of defect formation are as follows. When using the upper bound method, appearance dimple defect in the bottom

section in the final stage of the deformation process with combined radial-backward extrusion (Fig. 2, a), based on geometrical parameters, without affecting kinematical parameters has been shown. (the metal flow velocity in the vertical W and radial W_2 directions) [30]. On the other hand to analyze the problem of predicting defect in combined radial-backward extrusion can be used with the assumption of transition from combined to backward extrusion ($W_2 \rightarrow 0$). Metal flow in the radial direction that is defined as a condition to delay the moment of the dimple defect appearance. Thus, the geometrical parameters for predicting defect in combined radial-backward extrusion process as follows: H_0 – the height of billet, R_1 – the radius of the punch R_2 – the radius of matrix, R_3 – the geometrical position of the dimple, R – the radius of the fillet, h – the thickness of the flange, x – the width of the dimple, H_{cr} – the critical value of the bottom thickness in dimple appearance [30].




Figure 2. The calculated scheme of radial-backward extrusion process for predicting defect such as dimple: plane strain problem (a), axisymmetric problem (b)

Determination of the bottom thickness is the most valuable in the investigation of the defect solution

process in the form of dimple and accordingly, calculating the stroke of deformation process to define the moment of the dimple defect appearance. To determine the limiting bottom thickness will be used the solution of the equation as follows:

$$\left[(H_{cr} + G)^2 \cdot \left[\frac{(H_{cr} - G)(3H_{cr} + 2G)}{+ 2\mu_s G^2} \right] + \right. \\ \left. + GH_{cr} \cdot \left(\frac{3Gh + H_{cr}^2}{+(H_{cr} - h)^2 \left(1 - \frac{h}{R_2 - R_1} \right)} \right) \right] = 0 \quad (1)$$

where $G = R_2 - R_1 - h$.

The graphical dependence calculated by (1) makes it possible to determine the critical bottom thickness, to define the moment of the dimple defect appearance (Fig. 3) under the same as conditions of friction on the contact surface of the billet and the tool. Influence of friction conditions within the limits $\mu_s = 0 \div 0.16$ for cold extrusion process with $R_1 = 10$ mm, $R_2 = 20$ mm, in fig. 3 have been shown.

Different friction conditions and increase in flange thickness can be considered favorable factors to reduce the critical bottom thickness, i.e. different factors allow us to obtain dimple appearance after more time during deformation process. The obtained data must be compared with the investigation of the axisymmetric problem, finite element modeling results and experimental data.




Figure 3. Dependence of the bottom thickness H_{cr} from the flange thickness h under various friction conditions based on the upper bound method

When using the energy method of power balance, an approach for obtaining the critical values of the bottom thickness, which corresponds to the appearance of dimple defect (Fig. 2, b) [20, 29].

The value of the relative pressure is obtained in the equation:

$$\bar{p} = \bar{p}_{1-3} + \Delta\bar{p}_{c2-4} + \Delta\bar{p}_4, \quad (2)$$

where \bar{p}_{1-3} and $\Delta\bar{p}_4$ – relative pressures of modules 1-3 and 4, respectively, without taking into account the power of shear forces between modules 2 and 4;

$\Delta\bar{p}_{c2-4}$ – relative pressures of shear forces between modules 2 and 4.

The components of equation (2) are defined as follows:

$$\bar{p}_{1-3} = \left(\begin{aligned} &1 + \frac{1}{\sqrt{3}}(\bar{H}_0 - \Delta\bar{H}_X)(1 + \bar{W} + \bar{a}\bar{V}_1) + \bar{p}_2 + \\ &+ \frac{1 + \bar{a}^2 + 2\mu_{s \rightarrow}}{\sqrt{3}\bar{a}} \left(\frac{(\bar{M} + \bar{W}(1 - \bar{b}^2)) \ln\left(\frac{\bar{R}_2 + \bar{b}}{1 + \bar{b}}\right)}{-\frac{\bar{W}}{2}[(\bar{R}_2 - \bar{b})^2 - (1 - \bar{b})^2]} \right) + \\ &+ \frac{2(\mu_{s \uparrow} + \mu_{s \rightarrow})}{3\sqrt{3}(\bar{H}_0 - \Delta\bar{H}_X)} + \frac{4\mu_{s \uparrow}}{\sqrt{3}}(1 + \bar{W})(\Delta\bar{H}_X + \bar{l}_1) + \\ &+ \frac{4\mu_{s \uparrow}\bar{R}_2}{\sqrt{3}}\bar{W}(\bar{H}_0 - \bar{h} + \bar{l}_1) \end{aligned} \right) \quad (3)$$

$$\bar{p}_2 \leq \frac{2}{\sqrt{3}} \sqrt{\bar{a} \left(\frac{\bar{R}_2^3 - 1}{3} + \bar{b} \frac{\bar{R}_2^2 - 1}{2} \right) \times \left(4 \left(1 + \frac{\bar{a}^2}{3} \right) (\bar{U}_1 + \bar{U}_2) + \left(4 + \frac{\bar{a}^2}{3} \right) \bar{U}_3 \right)} \quad (4)$$

$$\Delta\bar{p}_{c2-4} = \bar{p}_{c2} = \frac{\bar{R}_2\bar{h}}{\sqrt{3}} \left(\bar{W} + \frac{\bar{M} + \bar{W}(1 - \bar{R}_2^2)}{2\bar{R}_2\bar{h}} \bar{a} \right) \quad (5)$$

$$\Delta\bar{p}_4 = \left[\frac{2}{\sqrt{3}} \left[\bar{M} + \bar{W}(1 - \bar{R}_2^2) \right] \ln\left(\frac{\bar{R}_2 + \bar{l}_2}{\bar{R}_2}\right) + \frac{4\mu_{s \rightarrow}}{\sqrt{3}} \left(\bar{M} + \bar{W}(1 - \bar{R}_2^2) \right) \frac{\bar{l}_2}{\bar{h}} \right] \quad (6)$$

where $\Delta\bar{H}_X = \frac{\Delta H_X}{R_1}$, $\bar{H} = \frac{H}{R_1}$, $\bar{H}_0 = \frac{H_0}{R_1}$, $\bar{R}_2 = \frac{R_2}{R_1}$,

$$\bar{h} = \frac{h}{R_1}, \bar{l}_1 = \frac{l_1}{R_1}, \bar{l}_2 = \frac{l_2}{R_1}, \bar{b} = \frac{\bar{h}}{\bar{a}} - \bar{R}_2, \bar{a} = \frac{\bar{H}}{1 - \bar{R}_2},$$

$$\bar{W} = \frac{W}{V_0}, \bar{V}_1 = \frac{1}{2(\bar{H}_0 - \Delta\bar{H}_X)}, \bar{M} = 2\bar{V}_1(\bar{H}_0 - \Delta\bar{H}_X).$$

In this case, the geometric position of dimple is not taken into account, the function of the relative pressure is investigated (2) from the relative velocity of metal outflow in the vertical direction.

The character of the change in the kinematic parameter (metal outflow rate in the vertical direction) is the criterion that, in the presence of a minimum point, make a conclusion about the possibility of a defect solution. The moment of defect formation corresponds to the presence of a minimum parameter \bar{W} depending on the bottom thickness H_{cr} (Fig. 4). For a process

without formation of dimple, is characterized by a monotonic fall over punch displacement (stroke), (growth relative to bottom thickness H_{cr}) the whole deformation process that is, the absence of a minimum point (fig. 4, lower curve with $\mu_{s \uparrow} = 0.16$, $\mu_{s \rightarrow} = 0$). We will carry out a comparative analysis of theoretical result by upper bound method (1), and energy method of power balance (2) from the viewpoint of investigation in the critical value of the bottom thickness, which corresponds to appearance of dimple defect. Using the range of variation in friction conditions for cold extrusion with $h_1=3$ mm and critical values range in the bottom thickness H_{cr} from 3.5 mm to 7.5 mm are considered. However, a comparative analysis with the upper bound method (Fig. 3) can be carried out only for the same as friction conditions on all contact surfaces of the billet and the tool, i.e. $\mu_s = \mu_{s \uparrow} = \mu_{s \rightarrow}$.




Figure 4. Change in the optimal value for the relative velocity of metal outflow in the vertical direction during the process punch displacement t from the bottom thickness

For values $h=3$ mm, the critical bottom thickness H_{cr} is determined by the upper bound method (1) with is approximately 5.93 mm (Fig. 3, the curve with $\mu_s = 0.08$) and in comparison by energy method of power balance H_{cr} is approximately 4.5 mm (solid curve with $\mu_{s \uparrow} = \mu_{s \rightarrow} = 10$, fig. 4). Similarly, for by equation (1) will be determined a critical bottom thickness is approximately 6.17 mm in comparison to 5 mm by the equation (2), and for the corresponding critical values reach 5.68 mm and 4.22 mm. Thus, the predicted value of H_{cr} , which is obtained by equation (1), can be used as a preliminary estimate of the same as friction conditions on all contact surfaces of the billet and the tool. In this case, the analysis of any other friction conditions ranges or changes in the configuration of the tool is impossible, however, the advantages of using (1) can definitely be attributed to the elementary nature of obtaining the necessary information. Comparative analysis with experimental data for the material lead is shown in the rationality of using equation (2), deviations of the predicted bottom thickness values with the beginning of dimple appearance from experimental result does not exceed 1-1.5 mm, and according to equation (1) it can reach 2.5 mm and higher [29]. Previously obtained results in this investigation were additionally compared

with the upper bound method that which showed more significant deviations from the experimentally obtained data. Thus, calculations by equation (2) are closer to reality and more informative from the viewpoint of taking into account various friction conditions and the possibility of promptly replacing the shape of the flange zone (configuration of the kinematic module 4, Fig. 2, b).

2.2 Computer simulation of the defect formation process with finite element method by QForm 2/3D program

A comparative analysis of the experimental result with obtained part from lead for the formation of dimple and simulation by QForm 2/3D in different parameters such as $R_1=10.5$ mm, $R_2=22.5$ mm, $h=3.5$ mm and $H_0=20.5$ mm and bottom thickness $H_{cr}=1,0$ mm are considered (Fig. 5). The obtained results in the shaping of the part are identical. This allows us to make more extensive use of simulation results by QForm 2/3D as an analogy a natural experiment for comparative analysis with obtained data by energy method of power balance. In this investigation the theoretical result according to equation (2) in the form $H_{cr}=4.5$ mm (fig. 4, curve with $\mu_{s\uparrow}=\mu_{s\rightarrow}=0.08$) confirms with experimental result 4 mm for mate-rial such as lead (fig. 5) for the moment of defect appearance.




Figure 5. Analytical report and models by QForm 2D/3D for appearance of dimple

According to simulation by QForm 2/3D, significant influence of friction conditions with the possibility of a defect such as dimple that is consistent with the result of theoretical investigations based on the calculation equation (2) are confirmed. Analysis of friction conditions as a technological factor in the shaping control of semi-finished product with lead material are carried out for parameters $R_1 = 10.5$ mm, $R_2 = 22.5$ mm, $h=3$ mm and $H_0=20$ mm and bottom thickness $H_{cr}= 4$ mm (Fig. 6) and partially higher when using equation (2) (Fig. 4). Thus, the conditions of contact friction can be attributed to significant factors affecting the possibility of defect formation in the process of combined radial-backward extrusion. It should be borne in mind that the deterioration of the friction conditions in the bottom section of the billet make it possible to reduce the size of the flange zone, and the deterioration of friction conditions on the glass wall, which are formed, against, will contribute to the increased dimensions of the flange and long-time delay for dimple appearance during deformation process.

However, the observance of the necessary friction conditions in the entire deformation process and constant for the entire contact surface of the billet and the tool are a rather controversial issue in the real process of extrusion.

As known, that combined extrusion processes with several freedom degrees of metal flow have the self-regulation property in the shaping of a semi-finished product. The presence of a complex configuration in the tool as chamfer and fillet forms are also factors for the control in the shaping of a semi-finished product. The results of shaping simulation in the extrusion process of combined radial-backward by Qform 2/3D indicate differences in the design of the flange zone (Fig. 7) and the possibility of correction with the provision of the defect appearance such as dimple. Varying the friction boundary conditions make it possible to obtain corrections of the filling in the flange zone up to 10% for the given parameters of the deformation process.




Figure 6. Process simulation by QForm 2/3D with defect appearance such as dimple under various conditions of friction

More favorable factor from the viewpoint of uniformity for filling the flange zone is the fillet selection factor that it is possible to form a uniform flange without defects. However, the primary task should be considered precisely the comparison in the shapes of the semi-finished product with the identification for the moment of defect appearance in the dimple form in billet (Fig. 1, c). In the process simulation by Qform 2/3D have been used additionally fillet radius dimensions such as 2 mm and 5 mm for $R_1=10.5$ mm, $R_2=22.5$ mm, $h=3$ mm and $H_0=20$ mm and friction conditions $\mu_1 = \mu_2 = 0.08$ for the lead material.

A delay in the dimple appearance can be reached approximately up to $(0.4 \div 0.5R)$ using the radius of fillet R . For a process without fillet in given geometric relationships we have the dimple appearance for a bottom thickness of approximately 4.4 mm, with the radius fillet 2 mm and 5 mm, it is possible to reduce this critical value by 3.231 mm and 2.023 mm, respectively.




Figure 7. Comparative analysis of glass bottom thickness that corresponds to the dimple appearance in $R = 5$ mm (left half) and $R = 2$ mm (right half)

Thus, for the tool design features fillet dimension is a favorable factor in terms of flange design and it is possible

to avoid dimple appearance. However, the possibility of correcting defect formation due to the design features of the tool by using chamfers and fillets with different dimensions on the tools such as matrix that before by energy method of power balance were not used, calculation models did not take into account these features.

2.3 Improvement of mathematical models for predicting defect formation process

The energy method of power balance allows us to use different schemes with the presence of kinematic modules with various configurations [33, 36-39].

Development of a kinematic module with fillet (Fig. 8) provides operational analysis capabilities to determine the optimal radius of fillet from viewpoint dimple appearance by the required amount in punch displacement (stroke) or bottom thickness [40]. The die and tool design to predict the defect formation such as dimple with the determination of the optimal fillet radius to make the production of quality parts will be main practical investigations.




Figure 8 – Kinematic module with fillet

The calculation scheme of the deformation process with module 4 – kinematic module Z4r with fillet, for anticipation dimple appearance, allows us to get the following results. According to equation (2) it is necessary to replace components (5) and (6) respectively (7) and (8) [40]:

$$\Delta \bar{p}_{c2-4r} = \left| \bar{p}_{c2} - \frac{2\pi^2 A}{\sqrt{3} R_2 R^2} \right|; \quad (7)$$

$$\Delta \bar{p}_{4r} = \left[\frac{1}{2\pi V_3 R_2 (h+R)} \sqrt{S \cdot V} + \frac{A}{2\sqrt{3} C^2} + \frac{2}{B} \left[R - \frac{A}{B} \ln \left| \frac{BC+A}{B \frac{R_2 R}{2\pi} + A} \right| \right] + \frac{2\mu S}{\sqrt{3}} \left[\frac{B^2}{A^2} \ln \left| \frac{(BR_2 R + 2\pi A)C}{R_2 R (BC+A)} \right| + A + \frac{B}{A} \left(\frac{1}{C} - \frac{2\pi}{R_2 R} \right) - \frac{1}{2} \left(\frac{1}{C^2} - \frac{4\pi^2}{R_2^2 R^2} \right) \right] \right]; \quad (8)$$

where, $S = \iiint_V \dot{\epsilon}_i^2 dV$, $\dot{\epsilon}_i$ – the intensity of deformation rates for the module Z4r;

$$V = 2\pi \left[A \left(R + R_2 \left(1 - \frac{R}{2\pi} \right) \ln \left| \frac{2\pi C}{R_2 R} \right| \right) + B \frac{(R_2 + R)^2 - R^2}{2} \right] - \text{the volume of the module Z4r for the approximating curve;}$$

$$z(r) = \frac{A}{r - R_2 \left(1 - \frac{R}{2\pi} \right)} + B$$

$$A = \frac{R^2 R_2}{2\pi} \left(1 + \frac{R_2}{2\pi} \right); \quad B = h + R - \frac{2\pi A}{R_2 R};$$

$$C = R \left(1 + \frac{R_2}{2\pi} \right); \quad V_3 = \frac{V_0 R_1^2}{2R_2 (h+R)}$$

Thus, the value of the relative pressure with the presence of the kinematic module Z4r taking into account (2) and (7) and (8) takes the form:

$$\bar{p} = \bar{p}_{1-3} + \Delta \bar{p}_{c2-4r} + \Delta \bar{p}_{4r} \quad (9)$$

According to equation (9) the influence of fillet for the dimple appearance with $R_1=10$ mm, $R_2=20$ mm, $h=3$ mm and $H_0=16$ mm is analyzed. For the basic calculation scheme of the process, the dimple appearance corresponds to the stroke $\Delta H_x=10.4$ mm (critical bottom thickness $H_{cr}=5.6$ mm, solid upper curve, Fig. 9), with the fillet it is possible to delay the dimple appearance with $R=2$ mm to $\Delta H_x=11.41$ mm ($H_{cr}=4.59$ mm) and $R=5$ mm to reduce $\Delta H_x=12.44$ mm ($H_{cr}=3.56$ mm). The obtained data correspond to the form of the semi-finished product, according to Qform2/3D (Fig. 7) and the oriented value of the delay in (0.4 ÷ 0.5R) mm.




Figure 9. Fillet influence analysis for dimple appearance

Thus, based on the comparative analysis by using energy method as upper bound method (1) and energy method of power balance (2) and (9), theoretical results indisputable will be confirmed. The use of dimple appearance in accordance with (1) can be recommended due to the simplicity of calculations in the form of a preliminary stage for predicting a defect. A more complete analysis, taking into account the identification of control factors in the form of friction conditions and the possibility of fillet in the flange zone, is provided by energy method of power balance.

3. CONCLUSIONS

Analysis of the possibilities for controlling the shaping of complexly shaped parts in the design stage of combined extrusion processes are associated with the development of theoretical methods.

The article provides a comparative analysis of two theoretical methods for predicting defect such as dimple by using the main modifications of the energy method. It was found that, in comparison with the experimental result, the upper bound method shows large deviations. Therefore, the use of estimate (1) is recommended as a preliminary stage for assessing defect formation for the simplest case without taking into account the radius of fillet on the matrix. Based on the analysis of a semi-finished product shaping in Qform 2/3D, a significant effect with the radius of fillet on the matrix and various friction conditions for the formation of a dimple were determined. It was found that ensuring more favorable friction conditions in the bottom part of the billet and in the flange zone in comparison with the friction conditions on the nozzle wall contributes to a more late appearance of dimple. To take these factors into account, the authors obtained new engineering calculations of the relative pressures (2) in the combined radial-backward extrusion process using a kinematic module with a fillet. It was found that the introduction of the fillet radius allows to delay the appearance of the dimple by a stroke equal to approximately $(0.4 \div 0.5R)$ mm for the entered radius of fillet R . This allow in the design stage, ensure that high-quality parts are obtained without the formation of a dimple by determining the required radius of fillet and friction conditions.

REFERENCES

- [1] Bhaduri, A.: Extrusion, Mechanical Properties and Working of Metals and Alloys, Springer Series in Materials Science, No. 264. pp. 599-646, 2018, doi: 10.1007/978-981-10-7209-3_13.
- [2] Plancak, M., Barisic, B., Grizelj, B.: Different possibilities of process analysis in cold extrusion, Key Engineering Materials, No. 367, pp. 209-214, 2008.
- [3] Markov, O.E., Kukhar, V.V., Zlygoriev, V.N., Shapoval, A.A., Khvashchynskiy, A.S., Zhytnikov, R.U.: Improvement of Upsetting Process of FourBeam Workpieces Based on Computerized and Physical Modeling, FME Transactions, Vol. 48, No. 4, pp. 946-953, 2020, doi: 10.5937/fme2004946M.
- [4] Shapoval, Alexander, et al.: Profitability of Production of Stainless Steel + Zirconium Metals Combination Adapters, Key Engineering Materials, Vol. 864, Trans Tech Publications, Ltd., Sept. 2020, pp. 285-291, doi: 10.4028/www.scientific.net/kem.864.285.
- [5] Salenko, Y., Puzyr, R., Shevchenko, O., Kulynych, V., Pedun, O.: Numerical Simulation of Local Plastic Deformations of a Cylindrical Workpiece of a Steel Wheel Rim, in: *Advances in Design, Simulation and Manufacturing III. DSMIE 2020. Lecture Notes in Mechanical Engineering*, pp. 85-94, doi:10.1007/978-3-030-50794-7_43.
- [6] Artiukh, V., Kukhar, V., and Balalayeva, E.: Refinement issue of displaced volume at upsetting of cylindrical workpiece by radial dies, in: *MATEC Web of Conferences*, Vol. 224, Article Number 01036, 2018, doi: 10.1051/mateconf/201822401036.
- [7] Markov, O. E., Gerasimenko, O. V., Kukhar, V. V., Abdulov, O. R., & Ragulina, N. V.: Computational and experimental modeling of new forging ingots with a directional solidification: The relative heights of 1.1, Journal of the Brazilian Society of Mechanical Sciences and Engineering, Vol. 41(8), 2019, doi:10.1007/s40430-019-1810-z.
- [8] Khrebtova, O.A., Shapoval, A.A., Mos'pan, D.V. et al.: Automatic Temperature Control System for Electric Resistance Annealing of Steel Welding Wire, Metallurgist, Vol.65, pp. 412-422, 2021, doi:10.1007/s11015-021-01171-4.
- [9] Markov, O.E., Aliiev, I.S., Aliieva, L.I., Hrudkina, N.S.: Computerized and physical modeling of upsetting operation by combined dies, Journal of Chemical Technology and Metallurgy, Vol. 55, No. 3, pp. 640-648, 2020.
- [10] Bohdanova, L. M., Vasilyeva, L. V., Guzenko, D. E., Kolodyazhny, V. M.: A Software System to Solve the Multi-Criteria Optimization Problem with Stochastic Constraints, Cybernetics and Systems Analysis, Vol. 54, No. 6, pp. 1013-1018, 2018. doi: 10.1007/s10559-018-0104-2
- [11] Chigarev, V. V., Belik, A. G., Gribkov, E. P., Gavrish, P. A.: A mathematical model of the process of rolling flux-cored tapes, Welding International, Vol.29, No 1, pp. 70-74, 2015, doi:10.1080/09507116.2014.888192.
- [12] Hrudkina, N.S.: Process modeling of sequential radial-direct extrusion using curved triangular kinematic module, FME Transactions, Vol. 49. No. 1, pp. 56-63, 2021, doi:10.5937/fme2101056H.
- [13] Filippov, Yu.K., Ignatenko, V.N., Golovina, Z.S., Anyukhin, A.S., Ragulin, A.V., and Gnevashev, D.A.: Theoretical study of the combined process of radial and backward extrusion in conical matrix [*Teoreticheskoe issledovanie kombinirovannogo protsessa radial'nogo vyidavlivaniya v konicheskoy matritse*], Kuznechno-Shtampovochnoe Proizvodstvo [*Obrabotka metallov davleniem*], No. 7., pp. 3-7, 2011. (in Russian).

- [14] Ogorodnikov, V.A., Dereven'ko, I.A., Sivak, R.I.: On the Influence of Curvature of the Trajectories of Deformation of a Volume of the Material by Pressing on Its Plasticity Under the Conditions of Complex Loading, *Materials Science*, No. 54 (3), pp. 326–332, 2018, doi: 10.1007/s11003-018-0188-x.
- [15] Perig, A. V. and Matveyev, I. A.: FEM-Based Deformation Regression Analysis of ECAE Strains, *FME Transactions*, Vol. 47, No. 4, pp. 851–855, 2019, doi:10.5937/fmet1904851P.
- [16] Dereven'ko, I. A.: Deformability and quality of blanks under conditions of combined shaping [*Deformiruemost' i kachestvo zagotovok v usloviyah kombinirovannogo formoizmeneniya*], in: *Materials working by pressure [Obrabotka metallov davleniem]*, Donbass State Engineering Academy, Kramatorsk, No. 3 (32), pp.80–86, 2012. (in Russian).
- [17] Winiarski, G. et al.: Theoretical and experimental analysis of a new process for forming flanges on hollow parts, *Materials*, Vol.13, No. 18: 4088, 2020, doi:10.3390/ma13184088.
- [18] Zhang, S.H., Wang, Z.R., Wang, Z.T., Xu, Y. and Chen, K.B.: Some new features in the development of metal forming technology, *Journal of Materials Processing Technology*, Vol. 151, No. 1-3, pp. 39–47, 2004, doi:10.1016/j.jmatprotec.2004.04.098.
- [19] Yang D.Y. and Kim K.J.: Design of Processes and Products through Simulation of Three-dimensional Extrusion, *J. Mater Process Technol.*, Vol. 191, pp. 2–6, 2007.
- [20] Hrudkina, N., Aliieva, L., Markov, O., Marchenko, I., Shapoval, A., Abhari, P., Kordenko, M.: Predicting the shape formation of hollow parts with a flange in the process of combined radial-reverse extrusion, *Eastern-European Journal of Enterprise Technologies*, Vol. 4, No. 1 (106), pp. 55–62, 2020, doi: 10.15587/1729-4061.2020.203988.
- [21] Kalyuzhnyi V.L., Aliieva, L.I., Kartamyshev, D.A. and Savchinskii, I.G.: Simulation of Cold Extrusion of Hollow Parts, *Metallurgist*, Vol. 61, No. 5–6, pp. 359–365, 2017, doi:10.1007/s11015-017-0501-1.
- [22] Zhang, S.H., Wang, Z.R., Wang, Z.T., Xu, Y. and Chen, K.B.: Some new features in the development of metal forming technology, *Journal of Materials Processing Technology*, Vol. 151, No. 1-3, pp. 39–47, 2004, doi:10.1016/j.jmatprotec.2004.04.098.
- [23] Farhoumand, A., Ebrahimi, R.: Experimental investigation and numerical simulation of plastic flow behavior during forward-backward-radial extrusion process, *Progress in Natural Science: Materials International*, Vol. 26, No 6, pp.650–656, 2016, doi: 10.1016/j.pnsc.2016.12.005.
- [24] Luri, R., Pérez, C.J. Luis: Modeling of the processing force for performing ECAP of circular cross-section materials by the UBM, *The International Journal of Advanced Manufacturing Technology*, No. 58, pp. 969–983, 2012, doi: 10.1007/s00170-011-3460-x.
- [25] Jafarzadeh, H., Zadshakoyan, M. and Abdi Sobbouhi, E.: Numerical studies of some important design factors in radial-forward extrusion process, *Materials and Manufacturing Processes*, Vol. 25, No. 8, pp. 857–863, 2010, doi: 10.1080/10426910903536741.
- [26] Lee, H.Y., Hwang, B.B., Lee, S.H.: Forming load and deformation energy in combined radial backward extrusion process, in: Mori, K., Pietrzyk, M., Kusiak, J. et al.: *Metal Forming 2012: proceedings of the 14th International Conference on Metal forming*, 16–19.09.2012, AGH University of Science and Technology, Krakow, pp. 487–490.
- [27] Aliieva, L. I.: Formation of defects in parts during cold extrusion processes [*Obrazovanie defektov detalej v processah holodnogo vydavlivaniya*], *Visnik HNTU. Herson*, No 4, pp. 18–27, 2016. (in Ukraine)
- [28] Savarabadi, M., Faraji, G., Zalnezhad, E.: Hydrostatic tube cyclic expansion extrusion (HTCEE) as a new severe plastic deformation method for producing long nanostructured tubes, *Journal of Alloys and Compounds*, No 785, pp. 163–168, 2019, doi: 10.1016/j.jallcom.2019.01.149.
- [29] Hrudkina, N., Aliieva, L. Abhari, P., Markov, O., Sukhovirska, L.: Investigating the process of shrinkage depression formation at the combined radial-backward extrusion of parts with a flange, *Eastern-European Journal of Enterprise Technologies*, Vol. 5, No. 1 (101), pp. 49–57, 2019, doi:10.15587/1729-4061.2019.179232.
- [30] Aliiev I., Aliieva L., Grudkina N. and Zhibankov I.: Prediction of the Variation of the Form in the Processes of Extrusion, *Metallurgical and Mining Industry*, Vol. 7, No. 3, pp. 17–22, 2011.
- [31] Perig, A.: Two-parameter Rigid Block Approach to Upper Bound Analysis of Equal Channel Angular Extrusion through a Segal 20-die, *Materials Research-Ibero-American Journal of Materials*, Vol. 18, No. 3, pp. 628–638, 2015, doi: 10.1590/1516-1439.004215.
- [32] Alyushin, Yu.A., Yelenev, S. A.: Theoretical foundations of energy methods for calculating metal forming processes [*Teoreticheskie osnovyi energeticheskikh metodov rascheta protsessov obrabotki metallov davleniem*], Rostov: RISHM, 1987. (in Russian).
- [33] Hrudkina, N., Aliieva, L., Markov, O., Malii, K., Sukhovirska, L., & Kuznetsov, M.: Predicting the shape formation of parts with a flange and an axial protrusion in the process of combined aligned radial-direct extrusion, *Eastern-European Journal of Enterprise Technologies*, Vol.5, No 1(107), pp. 110–117, 2020, doi:10.15587/1729-4061.2020.212018.
- [34] Chudakov, P.: Upper bound for the power of plastic deformation with a minimizing function [*Verhnyaya ocenka moshchnosti plasticheskoy deformatcii s ispol'zovaniem minimiziruyushchey funkicii*], *Izvestiya vuzov. Mashinostroenie*, No. 9, pp. 13–15, 1992 (in Russian).
- [35] Stepansky, L. G.: *Calculation of metal-forming processes [Raschetyi protsessov obrabotki metallov davleniem]*, Mashinostroenie, Moscow, 1979 (in Russian).

- [36] Hrudkina, N., Aliieva, L., Markov, O., Kartamyshv, D., Shevtsov, S., Kuznetsov, M.: Modeling the process of radial-direct extrusion with expansion using a triangular kinematic module, Eastern-European Journal of Enterprise Technologies, Vol. 3, No. 1 (105), pp. 17-22, 2020, doi: 10.15587/1729-4061.2020.203989.
- [37] Aliieva L., Hrudkina N., Aliiev I., Zhdankov I. and Markov O.: Effect of the tool geometry on the force mode of the combined radial-direct extrusion with compression, Eastern-European Journal of Enterprise Technologies, Vol. 2, No. 1 (104), pp. 15-22, 2020, doi:10.15587/1729-4061.2020.198433.
- [38] Aliieva, Leila I., Markov, Oleg E., Aliiev, Igramotdin S., Hrudkina, Natalia S., Levchenko, Vladymyr N., Malii, Khrystyna V.: Analysis of Power Parameters of Combined Three-Direction Deformation of Parts with Flange, FME Transactions, Vol. 49, No. 2, pp. 344-355, 2021, doi: 10.5937/fme2102344A.
- [39] Hrudkina, N., Aliieva, L., Abhari, P., Markov, O., Sukhovirska, L.: Investigating the process of shrinkage depression formation at the combined radial-backward extrusion of parts with a flange, Eastern-European Journal of Enterprise Technologies, Vol. 5, No. 1 (101), pp. 49-57, 2019, doi:10.15587/1729-4061.2019.179232.
- [40] Hrudkina, N., Aliiev, I., Markov, O., Savchenko, I., Sukhovirska, L., Tahan, L.: Designing a kinematic module with rounding to model the processes of combined radial-longitudinal extrusion involving a tool whose configuration is complex, Eastern-European Journal of Enterprise Technologies, Vol. 2, No. 1(110), pp. 81–89, 2021, doi:10.15587/1729-4061.2021.227120.

NOMENCLATURE

V_0	Punch velocity, [mm/s]
V_3	Velocity of the metal flow for the module Z4r, [mm/s]
W	Velocity of the metal flow in the vertical direction on the glass wall, [mm/s]
h	The thickness of the flange, [mm]
H_{cr}	The critical value of the bottom thickness in dimple appearance, [mm]
ΔH_x	Punch displacement (stroke), [mm]
R_1	The radius of the punch, [mm]
R_2	The radius of matrix, [mm]
R_3	The geometrical position of the dimple, [mm]
R	The radius of fillet
$z(r)$	Inclined boundary of the flow interface in module 2

μ_s	Coefficient of friction, $0 \leq \mu_s \leq 0.5$
\bar{p}	Relative pressure
\bar{p}_r	Relative pressure with radius of fillet
\bar{p}_{1-3}	Relative pressure in modules 1-3 and 4
$\Delta \bar{p}_4$	Relative pressure in modules 4
$\Delta \bar{p}_{4r}$	Relative pressure in modules 4 with radius of fillet
$\Delta \bar{p}_{c2-4}$	Relative pressure of shear force between modules 2 and 4
$\Delta \bar{p}_{c2-4r}$	Relative pressure of shear force between modules 2 and 4 with radius of fillet

МАТЕМАТИЧКА И КОМПЈУТЕРСКА СИМУЛАЦИЈА ПОЈАВЕ УДУБЉЕЊА ТОКОМ ХЛАДНОГ КОМБИНОВАНОГ ИЗВЛАЧЕЊА

Н.С. Хрудкина, О.Е. Марков, А.А. Шаповал,
В.А. Титов, И.С. Алијев, П. Абхари, К.В. Малиј

Овај чланак представља компаративну анализу за предвиђање дефекта као што је удубљење енергетским методом биланса снага, методом горње границе и методом коначних елемената. Метода горње границе узима у обзир геометријску позицију и димензију удубљења, критеријум за формирање у удубини енергетским методом биланса снаге је присуство минималне тачке у функцији релативног притиска на релативну брзину изливања метала у вертикални правац. Нови инжењерски прорачуни за релативни притисак су развијени у комбинованом процесу извлачења радијално-назад коришћењем кинематичког модула са углом. Урађена је упоредна анализа добијених података енергетским методом биланса снага, методом горње границе, компјутерском симулацијом Kform 2/3D програмом и експерименталним подацима. Утврђена је рационалност употребе енергетског метода биланса снага с обзиром на његову ефикасност и могућност узимања у обзир различитих услова трења и присуства заобљења на матрици, као и мањих одступања од резултата симулације коначних елемената и експерименталних података дефинисано. Обезбеђивање више услова који су повољни за трење у дну гредице и у области прирубнице у поређењу са условима трења на стакленом зиду доприноси одлагању изгледа удубљења. Утврђено је да радијус угаонице омогућава одлагање појаве удубљења за приближно $(0,4 \div 0,5P)$ мм за унети радијус угаонице P . То нам омогућава да проширимо могућности добијања делова са прирубницом за комбиновано извлачење радијално-назад без формирања дефекта као што је удубљење.